

<p>ColorPrint™ PU</p> <p></p> <p>Applies to:</p> <ul style="list-style-type: none"> • 100% cotton • Poly/cotton blends • 100% polyester • Leather • Lycra®/spandex <p>How to Apply:</p> <ul style="list-style-type: none"> • Set heater/dryer to 113°F/45°C-122°F/50°C • If heavy saturation ink, dry 1 hour before cutting • Print, cut and weed material • Mask with TTD Easy or TTD High Tack Mask <p style="text-align: center;">295° F/146° C Medium Pressure 15-20 seconds Peel Hot</p> <p>Laundering:</p> <ul style="list-style-type: none"> • Wait 24 hours before first wash • Machine wash warm or cold / mild detergent • Do not bleach or dry clean • Dry on normal setting <p><small>Compatible with Eco Solvent and Solvent based inks</small></p> <p>Blade: 45°/60° Composition: PU Microns/Mils: 70/2.8</p>	<p>ColorPrint™ Soft</p> <p></p> <p>Applies to:</p> <ul style="list-style-type: none"> • 100% cotton • Poly/cotton blends • 100% polyester • White or light colors only <p>How to Apply:</p> <ul style="list-style-type: none"> • Perform a test cut • Print in positive, cut, and weed material • Allow 30 mins. to 1 hour dry time • No masking required! <p><small>Peel carrier after 15 seconds but not longer than 1 minute. If you wait longer, press shirt again and peel warm after waiting 15 seconds</small></p> <p style="text-align: center;">311° F/155° C Medium Pressure 10-15 seconds Peel warm</p> <p>Laundering:</p> <ul style="list-style-type: none"> • Wait 24 hours before first wash • Machine wash warm or cold / mild detergent • Do not bleach or dry clean • Dry on normal setting <p><small>Compatible with Eco Solvent and Solvent based inks</small></p> <p>Blade: 45°/60° Composition: PU Microns/Mils: 30/1.2</p>	<p>ColorPrint™ Soft Opaque</p> <p></p> <p>Applies to:</p> <ul style="list-style-type: none"> • 100% cotton • Poly/cotton blends • 100% polyester • Lycra®/spandex • Leather <p>How to Apply:</p> <ul style="list-style-type: none"> • Set heater/dryer to 113°F/45°C-122°F/50°C • Print, cut and weed material • Allow to dry 30 min. to 1 hour for most designs • Mask with TTD Easy or TTD High Tack Mask <p><small>Soft Opaque is a very thin material. Cutter force should be between 30-50 grams to insure that the design will remove with the mask. Keep room 70°F or below.</small></p> <p style="text-align: center;">311° F/155° C Medium Pressure 15 seconds Peel hot</p> <p>Laundering:</p> <ul style="list-style-type: none"> • Wait 24 hours before first wash • Machine wash warm or cold / mild detergent • Do not bleach or dry clean • Dry on normal setting <p><small>Compatible with Eco Solvent and Solvent based inks</small></p> <p>Blade: 45°/60° Composition: PU Microns/Mils: 45/1.7</p>
<p>ColorPrint™ Easy</p> <p>Applies to:</p> <ul style="list-style-type: none"> • 100% cotton • Poly/cotton blends • 100% polyester • Leather • Lycra®/spandex <p>How to Apply:</p> <ul style="list-style-type: none"> • Print, cut and weed material - no dry time! • Mask image with TTD Easy Mask <p style="text-align: center;">300° F/149° C Medium Pressure 15 seconds Peel warm</p> <p>Laundering:</p> <ul style="list-style-type: none"> • Wait 24 hours before first wash • Machine wash warm or cold / mild detergent • Do not bleach or dry clean • Dry on normal setting <p><small>Compatible with Eco Solvent and Solvent based inks</small></p> <p>Blade: 45°/60° Composition: PU Microns/Mils: 80/3.1</p>	<p>ColorPrint™ Extra</p> <p>Applies to:</p> <ul style="list-style-type: none"> • 100% cotton • Poly/cotton blends • 100% polyester • Nylon • Leather <p>How to Apply:</p> <ul style="list-style-type: none"> • Print, cut and weed material • Allow to dry 30 mins. to 1 hour before masking • Mask image with TTD Easy Mask <p style="text-align: center;">320° F/160° C Medium Pressure 10-15 seconds Peel hot</p> <p>Laundering:</p> <ul style="list-style-type: none"> • Wait 24 hours before first wash • Machine wash warm or cold / mild detergent • Do not bleach or dry clean • Dry on normal setting <p><small>Compatible with Eco Solvent, Solvent and Latex based inks</small></p> <p>Blade: 45°/60° Composition: PVC Microns/Mils: 135/5.3</p>	<p>ColorPrint™ Sublithin</p> <p></p> <p>Applies to:</p> <ul style="list-style-type: none"> • 100% cotton • Poly/cotton blends • 100% polyester • sublimated polyester • Leather <p>How to Apply:</p> <ul style="list-style-type: none"> • Set heater/dryer to 113°F/45°C-122°F/50°C • Print, cut and weed material • Mask with TTD Easy Mask <p style="text-align: center;">265° F/130° C Medium Pressure 20 seconds Peel warm</p> <p>Laundering:</p> <ul style="list-style-type: none"> • Wait 24 hours before first wash • Machine wash warm or cold / mild detergent • Do not bleach or dry clean • Dry on normal setting <p><small>Compatible with Eco Solvent and Solvent based inks</small></p> <p>Blade: 45°/60° Composition: PU Microns/Mils: 110/4.3</p>

Recommended Accessories: TTD Easy Mask, TTD High Tack Mask, Siser weeder squeegee, multipurpose paper, heat transfer cover sheet

Install the Siser App (and enable push notifications) for all the latest and greatest HTV info! Simply search Siser north America in your app store or scan the QR code below



*Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.