

EasyWeed®

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyWeed® Extra

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal setting

EasyWeed® Electric

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyWeed® Stretch (matte)

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 15 seconds
- Peel carrier hot or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal setting

EasyWeed® Sub Block

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 265°F / 130°C
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Hang item to dry

EasyWeed® Adhesive

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier hot

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 275°F / 135°C
- Use medium pressure for 5-10 seconds
- Peel carrier hot
- Apply top layer

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyPatterns®

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut design (do not mirror). weed then mask
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold
- Cover and reheat for 2-3 seconds

Laundrying:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

EasyReflective®

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather | Lycra®/Spandex



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 15 seconds
- Peel carrier warm (wait at least 15 seconds)
- Cover and reheat for 2-3 seconds

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Recommended Accessories:

Siser Weeder, parchment or multipurpose paper, or heat transfer cover sheet

* Due to variances in the manufacturing process of fabrics, Siser highly recommends testing prior to production.

Blackboard™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier warm or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 275°F / 135°C
- Use light/medium pressure for 15 seconds
- Peel carrier warm or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Glitter

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier warm

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C
- Use medium pressure for 15-20 seconds
- Peel carrier warm

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Holographic

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C
- Use medium pressure for 15-20 seconds
- Peel carrier cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

Metal

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5-10 seconds. • Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 10-15 seconds
- Peel carrier cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash cold with mild detergent
- Do not bleach or dry clean
- Hang item to dry

StripFlock® Pro

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier hot or cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C
- Use medium pressure for 10-15 seconds
- Peel carrier hot or cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on normal dryer setting

StripFlock®

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather

Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 15-20 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 320°F / 160°C
- Use medium/firm pressure for 15-20 seconds
- Peel carrier cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on low dryer setting

Brick® 600

For Use On: 100% cotton | Poly/cotton blends | 100% polyester



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier cold

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 311°F / 155°C
- Use medium/firm pressure for 20 seconds
- Peel carrier cold

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Dry on low dryer setting

ReflectAll™

For Use On: 100% cotton | Poly/cotton blends | 100% polyester | Leather | Lycra®/Spandex



Application Instructions (Home Iron):

- Set iron dial between Cotton and Linen
- Cover design with Kraft paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure for 10-15 seconds
- If areas of design lift after application, replace cover sheet and re-press for 10 seconds. • Peel carrier hot

Application Instructions (Heat Press):

- Cut in reverse and weed excess material
- Preheat garment for 2-3 seconds
- Apply design at 305°F / 150°C
- Use medium pressure for 5 seconds
- Peel carrier hot
- Cover and reheat for 10 seconds

Laundrying:

- Wait 24 hours before first wash
- Machine wash warm or cold with mild detergent
- Do not bleach or dry clean
- Hang item to dry